



Oberflächenveredelung GmbH

ENVIRAL® Oberflächenveredelung GmbH · Altdorfer Weg 6 · D-14823 Niemege

Wir danken für Ihr Vertrauen!

Altdorfer Weg 6 | info@enviral.de
D-14823 Niemege | www.enviral.de

Telefon +49 (0) 33843 642-04
Telefax +49 (0) 33843 642-24

kostenlose Servicenummer
0-800/ENVIRAL 0-800/368 47 25

All technical recommendations for application we give to our clients to the best of our knowledge and according to the state of the art are not binding. According to our General Terms and Conditions of Business they do not establish any contractual legal relationship and no ancillary obligations resulting from the purchase contract. This does not release the client from his/her own responsibility to check our services, products and recommendations with regard to their suitability for the intended use. Our General Terms and Conditions of Business apply, which you can view at any time at www.enviral.eu.

DATA SHEET

ENV 302 – Powder coating

Substrate material:

STEEL galvanized

Component measurements:

larger l = 6,500 x w = 800 x h = 1,800 mm
up to l = 13.600 x w = 2.500 x h = 4.000 mm
up to l = 17.500 x w = 1.000 x h = 2.000 mm

Interior application

(for smaller parts see data sheet ENV 301)

Component weight:

up to 3,000 kg

Process:

Sweeping/fine blasting and powder coating

Product description:

Surface pre-treatment and surface coating on a lead-, chromium-, cadmium- and solvent-free basis

Properties:

- Large selection of effects
- Best mechanical properties
- Good flow
- Chromium-, lead-, cadmium- and solvent-free

Application:

Coating of galvanized steel profiles, steel sheets and steel constructions for interior application

03 / 2022

ENV 302 / page 1

Geschäftsführer Ing. Rainer Rogovits
Amtsgericht Potsdam HRB 7819
Ust.-IdNr. DE 166554396
St.-Nr. 048/108/03245

Bankverbindungen Berliner Sparkasse · BIC BELA2E33XXX
IBAN DE79 1005 0000 6610 0036 86
VR-Bank Fläming eG · BIC GENODEF1LUK
IBAN DE37 1606 2008 4105 6930 00



Process restrictions:

Cavities, sharp edges and concealed areas (e.g. doublings) cannot be protected. Galvanized surfaces must be in perfect condition and have a coatable surface, in other words free of zinc corrosion, water-soluble salts, passivation, zinc sprays, zinc pastes or similar separation layers. Nevertheless, outgassing and bubble formation may occur due to the thermal treatment after coating.

When producing the parts, it is necessary to ensure that machining fluids and greases (especially around non-visible areas, unavoidable doublings, blind holes, threads, etc.) are removed, as these cannot be completely cleaned off by the sweeping/fine blasting process and therefore have a negative effect on the powder coating layer and durability during the curing process.

Due to sweeping/fine blasting, finest pinhole-like surface inclusions can occur in the powder-coated surface. This effect can be avoided by double coating. A separate order is necessary.

In deviation from the DIN 55633 standard, **no** optical improvement of the zinc coating (no removal of thickenings and irregularities in the zinc coating) is carried out by ENVIRAL® before powder coating of galvanized surfaces. This is a chargeable additional service that requires an agreement and a separate written order by the customer.

Color tones:

- Approx. 180 RAL colors (smooth glossy, smooth satin finish, smooth matt, (coarse) textured glossy)
- Standard RAL colors also available as ENV Antimicrobial
- Metallic, approx. P-tones, approx. DB metallic
- Pearlescent mica metallic
- Special color tones NCS; Sikkens or according to color samples
- Effect powder coatings: ENVnatuRAL Design, ENVTransparent, etc.

Process description:

- Sweeping / fine blasting (compare with data sheet ENV 700)
- Powder coating
- Curing

Notes:

Residues of blasting media in component cavities are to be expected! These cannot be completely removed. - Please take this into account when further processing and completing your components (e.g. protection of mechanical/movable built-in parts).

Assessment of the surface:

The finished coated surface is assessed in accordance with the Association of Window and Facade Manufacturers (Verband der Fenster- und Fassadenhersteller e.V.), VFF leaflet ST.02, status August 2016 (Visual assessment of organically coated surfaces on steel) and delivered in this quality. Additional requirements, including standard requirements or requirements of service specifications, are only valid if they have been explicitly confirmed in writing by ENVIRAL®.

Suspension:

According to our suspension recommendations (compare data sheet ENV 800)

Quality assurance:

Continuing process control and order-specific quality assurance, destructive and non-destructive

Packaging:

Noppa foam, air cushion film

Repair:

According to our repair recommendations (compare data sheet ENV 802)

Cleaning:

According to our cleaning recommendations (compare data sheet ENV 801)

Sealant adhesion:

According to sealant adhesion on powder-coated surfaces of facades (compare data sheet ENV 803)

Approvals:

Environmental Product Declaration according to ISO 14025 and EN 15804:

EPD-VDL-20160263-IAG1-EN: Polyester powder coating

EPD-VDL-20160264-IAG1-EN: Epoxy powder coating

EPD-VDL-20160265-IAG1-EN: Hybrid powder coating

EPD-GDA-20190070-IBH1-EN: Aluminum profile coated