



Oberflächenveredelung GmbH

ENVIROAL® Oberflächenveredelung GmbH · Altdorfer Weg 6 · D-14823 Niemege

Wir danken für Ihr Vertrauen!

Altdorfer Weg 6 | info@enviral.de
D-14823 Niemege | www.enviral.de

Telefon +49 (0) 33843 642-04
Telefax +49 (0) 33843 642-24

kostenlose Servicenummer
0-800/ENVIROAL 0-800/368 47 25

All technical recommendations for application we give to our clients to the best of our knowledge and according to the state of the art are not binding. According to our General Terms and Conditions of Business they do not establish any contractual legal relationship and no ancillary obligations resulting from the purchase contract. This does not release the client from his/her own responsibility to check our services, products and recommendations with regard to their suitability for the intended use. Our General Terms and Conditions of Business apply, which you can view at any time at www.enviral.eu.

DATA SHEET

ENV 303 – Powder coating

Substrate material:

STEEL galvanized

Component measurements:

up to l = 6,500 x w = 800 x h = 1,800 mm

Exterior application

(for larger parts see data sheet ENV 304)

Component weight:

up to 250 kg

(for higher unit weights see data sheet ENV 304)

Process:

Degreasing / phosphating, ENVIROAL® curing primer and powder coating

Product description:

Surface pre-treatment and surface coating on a lead-, chromium-, cadmium- and solvent-free basis

Properties:

Pre-treatment chemistry and powder coating are tested and approved by the "Gütegemeinschaft für Stückgutbeschichtung".

- Highest weather resistance
- Best mechanical properties
- Good flow
- Chromium-, lead-, cadmium- and solvent-free

Application:

Coating of galvanized steel profiles, steel sheets and steel constructions for exterior application

03 / 2022

ENV 303 / page 1

Geschäftsführer Ing. Rainer Rogovits
Amtsgericht Potsdam HRB 7819
Ust.-IdNr. DE 166554396
St.-Nr. 048/108/03245

Bankverbindungen Berliner Sparkasse · BIC BELADEV333
IBAN DE79 1005 0000 6610 0036 86
VR-Bank Fläming eG · BIC GENODEF1LUK
IBAN DE37 1606 2008 4105 6930 00



Process restrictions: Cavities, sharp edges and concealed areas (e.g. doublings) cannot be protected.
Galvanized surfaces must be in perfect condition and have a coatable surface, in other words free of zinc corrosion, water-soluble salts, passivation, zinc sprays, zinc pastes or similar separation layers. Nevertheless, outgassing and bubble formation may occur due to the thermal treatment after coating.

In deviation from the DIN 55633 standard, **no** optical improvement of the zinc coating (no removal of thickenings and irregularities in the zinc coating) is carried out by ENVIRAL[®] before powder coating of galvanized surfaces. This is a chargeable additional service that requires an agreement and a separate written order by the customer.

Color tones:

- Approx. 180 RAL colors (smooth glossy, smooth satin finish, smooth matt, (coarse) textured glossy)
- Standard RAL colors also available as ENV Antimicrobial
- Metallic, approx. P-tones, approx. DB metallic
- Pearlescent mica metallic
- Special color tones NCS; Sikkens or according to color samples
- Effect powder coatings: ENVnatuRAL Design, ENVTransparent, etc.

Process description:

- Phosphating or Sweeping (compare with data sheet ENV 700)
- ENVIRAL[®] curing primer
- Curing
- Powder coating
- Curing

Notes: **Residues of blasting media in component cavities are to be expected! These cannot be completely removed. - Please take this into account when further processing and completing your components (e.g. protection of mechanical/movable built-in parts).**

Assessment of the surface: The finished coated surface is assessed in accordance with the Association of Window and Facade Manufacturers (Verband der Fenster- und Fassadenhersteller e.V.), VFF leaflet ST.02, status August 2016 (Visual assessment of organically coated surfaces on steel) and delivered in this quality. Additional requirements, including standard requirements or requirements of service specifications, are only valid if they have been explicitly confirmed in writing by ENVIRAL[®].

Suspension: According to our suspension recommendations (compare data sheet ENV 800)

Quality assurance: Continuing process control and order-specific quality assurance, destructive and non-destructive

- Packaging:** Noppa foam, air cushion film
- Repair:** According to our repair recommendations (compare data sheet ENV 802)
- Cleaning:** According to our cleaning recommendations (compare data sheet ENV 801)
- Sealant adhesion:** According to sealant adhesion on powder-coated surfaces of facades (compare data sheet ENV 803)
- Approvals:** Environmental Product Declaration according to ISO 14025 and EN 15804:
EPD-VDL-20160263-IAG1-EN: Polyester powder coating
EPD-VDL-20160264-IAG1-EN: Epoxy powder coating
EPD-VDL-20160265-IAG1-EN: Hybrid powder coating
EPD-GDA-20190070-IBH1-EN: Aluminum profile coated